

## 5.10 Pipe Materials for Specified Uses

Revision: October 23, 2012

Table 5-9 shows pipe materials for specified uses.

**Table 5-9. Pipe materials for specified uses.**

Pipe Material and Specification <sup>a</sup>	Function				
	House to Tank <sup>b</sup>	Tank to Dosing Chamber	Tanks to Drainfield <sup>c,d</sup>	Gravity Drainfield <sup>c,d</sup>	Pressure Distribution System
ABS Sch. 40 <sup>e</sup>	ASTM D2661	X	X	X	X
	ASTM F628	X	X	X	X
PVC	ASTM D3034 <sup>f</sup>	X	X	X	
	ASTM D2729			X	
	ASTM D2241	X	X	X	X
	AWWA C900	X	X	X	X
	ASTM D2665	X	X	X	
	ASTM D1785	X	X	X	X
PE	AWWA C906	X	X	X	X
	ASTM F810 <sup>g</sup>		X	X	
	ASTM F405 <sup>h</sup>			X	

*Notes:* polyvinyl chloride (PVC); acrylonitrile-butadiene-styrene (ABS); polyethylene (PE); American Society for Testing and Materials (ASTM); American Water Works Association (AWWA)

a. Or equivalent materials as specified by ASTM or AWWA.

b. See State of Idaho Division of Building Safety, Plumbing Bureau.

c. Specified in section 3.2.2 of the *Technical Guidance Manual for Individual and Subsurface Sewage Disposal Systems* (TGM).

d. Must use ASTM D3034 or equivalent as specified in 3.2.3 of the TGM. ASTM D3033 piping was previously approved for use spanning the tank to dosing chamber, tank to drainfield, and in the drainfield.

e. ABS Schedule 40 or piping material of equal or greater strength. Required by IDAPA 58.01.03.007.21.a.

f. Excavation must be compacted with fill material to 90% standard proctor density, with a minimum of 12 inches of cover material. Required by IDAPA 58.01.03.007.02.b.

g. Smooth wall high-density polyethylene (HDPE), white suitable for effluent and drainfield piping.

h. Corrugated HDPE, black with stripe, flexible, suitable for drainfield piping.